
9905H-PF Reflective Heat Transfer Film - Perforated

GIOLITE 9905H-PF has a glass beads layer on top and the surface of it is protected by a PET carrier. A plastic liner on the adhesive side is removed before applying the tape to the fabric. The perforated holes make the film breathable and unique which differentiates the design from traditional style of plain trim.





PF-1 PF-2

COMPOSITION

Glass Bead	30%
Resin	30%
Hotmelt Glue	30%
Others	10%

RETROREFLECTIVE PERFORMANCE

Observation Angle	Entrance Angle	Test result (cd / lux.m2)	Minimum coefficient of Retro-reflection in cd / lux.m2	
12′	5°	460	330	

PHYSICAL PERFORMANCE AFTER TEST EXPOSURE

After abrasion EN530:1991 Method 2, - 5,000 rubs
After flexing ISO 7854: 1984, Method A, 7,500 cycles

After folding at cold temperature ISO 4675, (20°±1)°C

After temperature variation 12 hours @ $50\pm2^{\circ}$ C, 20 hours@- $30\pm2^{\circ}$ C. cond.>2 hrs.

After washing ISO 6330: 1984 Method 2A@60°C; dried stress-free at 50+/-5°C.

50 cycles

After dry cleaning ISO 3175 : 1979 method 9.1 – 50 cycles

APPLICATION INSTRUCTIONS

Cutting Die-cut, hand-cut, slit

Heat transfer Work on a flat surface where garment heat and pressure can be applied.

Do not heat transfer over seams and stitches. (150°C for 8 seconds)

GUIDELINE FOR WORKING CONDITIONS

> The proper temperature, pressure, time must be checked in advance with the fabrics which the film is applied to.

Nylons and DWR (Durable Water Repellent) finished fabrics are not recommended to use.

CARE INSTRUCTIONS FOR THE FINISHED PRODUCT





> Washing

Washer : Standard Household Washing Machine

Temperature : 60°C

Detergent : Standard Household Detergent Setting : Colored Clothing without Pre-wash

Maximum washing time on highest temperature not to exceed 12 minutes.

Maximum total washing time not to exceed 50 minutes.

Test fabric for dye migration.

> Bleaching

Not Recommended

> Drying

Tumble Dry Low

> Ironing

Do not use steam, use a cool or warm temperature setting, avoid direct contact of the reflective surface when ironing, use a press cloth.

SPECIFICATION

Hole Size	Width	Roll Length	Q'ty / Carton	Weight / Carton	Volume / Carton
1mm (PF-1)	50 mm	50 MTS	1,200 MTS	28 KGS	0.039 CBM
2mm (PF-2)	50 mm	50 MTS	1,200 MTS	26 KGS	0.039 CBM

STORAGE

- > Keep away from the direct sunlight, hot and humid place.
- ➤ Use it within 1 year from the date of the lot number (production date).

GIOLITE LUMIAN Co., LTD

RM408, Woolim E Biz Center #1, 170-5, Guro-Dong, Guro-Gu, Seoul, KOREA

Tel: +82-2-869-1988(Rep.) Fax: +82-2-869-7711

email: giolite@giolite.com
Website: www.giolite.com