



Approved by
R. D. S. O
IRS CLASS - I
L & T

ANAND MIG-1
Copper Coated
MIG Welding Wire

Description

ANAND MIG-1 is a double deoxidised Copper Coated MIG Welding Wire for general engineering and structural applications. The cast, helix tensile strength and chemistry of the wire are controlled to yield high quality welds with least spatter.

Typical Applications

It is ideally suited for continuous welding of unalloyed and structural steels. Finds extensive use in the automobile and container industry. Also used for welding bicycle frames. Railways bogies earth moving equipments etc.

Classifications

AWS : A 5.18 ER 70S - 6
IS : 6419

**Welding Current (Amps.)
DC (+)**

Size (mm)	0.8	1.0	1.2	1.6
Amps	50 - 160	80 - 200	110 - 250	200 - 400

**Weld
Metal Analysis (%)**

C	Mn	Si	S	P
0.08	1.50	0.80	0.016	0.018

**Typical Mechanical
Properties**

UTS (mpa (N/mm ²))	YS (mpa (N/mm ²))	EL %	CVN Impact at - 30°C (Kg/m)
585	455	26.0	5.0

Packing Specifications

Spool of 12.5 Kg. Nett. Wt. In Moisture resistant packing
Drum Packing available.

ANAND ARC LTD.

(AN ISO 9001 COMPANY)

30, Kala Udyog, L.B.S. Marg, Bhandup, Mumbai-400 078

Tel. : 2566 1853 / 2566 1788 / 2566 4340 / 2566 4321

Fax : 2566 2833

Email : anand@bom5.vsnl.net.in / sales@anandarc.com

Site : www.anandarc.com

ANAND ARC PRODUCTS

More than a Source, a Solution



ANAND MIG-4
Low Alloy Steel Wire for
Gas Shielded Arc Welding

Technical Data

Description: ANAND MIG - 4 contain a high level of deoxidizers (Mn and Si), to control porosity when welding with CO₂ as the shielded gas and molybdenum for increased strength. It will give radio graphic quality welds with excellent bead appearance in both ordinary and difficult-to-weld carbon and low alloy steels.

Typical Application: The combination of weld soundness and strength marks ANAND MIG - 4 suitable for single and multiple pass welding of verity of carbon and low alloy steels.

Classification: AWS: A5.28 ER 90SD2

Welding Current (Amps) AC/DC (+)	0.8mm 50-160	1.0mm 80-200	1.2mm 110-250	1.6mm 200-400
---	-----------------	-----------------	------------------	------------------

Chemical Analysis (%)	C	Mn	Si	Mo	Cu	S	P
	0.07 to 0.12	1.60 to 2.10	0.50 to 0.80	0.40 to 0.60	0.20 to 0.40	0.025 max	0.025 max

Mechanical Properties Of All Weld Metal	UTS N/mm ² 620MPa (min)	Y.S N/mm ² 540MPamin	% EL L=5d 17 min	CVN Impact at -29°C=27J(min) -20°C=47J(min)
--	--	---------------------------------------	------------------------	--

Packing Specification Spool of 12.5 Kg. Nett. Wt. In moisture resistant packing.

ANAND ARC LTD.
(AN ISO 9001:2008 COMPANY)

701, Trade Centre Bandra Kurla Complex (BKC),
Bandra (E), Mumbai - 400 051.
Tel: +91-22-42688484, Fax: +91-22-42688400
E-mail : sales@anandarc.com / anand@anandarc.com
Website : www.anandarc.com

ANAND ARC PRODUCTS
More than a Sources, a Solution.



ANAND TIG-2
Copper Coated cut length solid
wire for TIG welding

Technical Data

Description: **ANAND TIG - 2** is a triple deoxidised (silicon, manganese, aluminum) mild steel wire. It will give radiographic quality welds with minimum spatter and smooth flow, stable arc under optimum conditions.

Typical Application: **ANAND TIG-2** is recommended for high quality pipe welding of mild and medium tensile steels and is ideal for root passes in thick walled material.

Classification: AWS: A5.18 ER 70S-2

Sizes : 1.60mm 2.00mm 2.50mm 3.15mm 4.00mm

Typical Wire Analysis (%)

C	Mn	Si	S	P	Cr	Mo	Ni	Cu	V	Ti	Al	Zr
0.07	0.9	0.40	0.035	0.025	0.15	0.15	0.15	0.50	0.03	0.05	0.05	0.02
Max	1.40	0.70	Max	Max	Max	Max	Max	Max	Max	0.15	0.15	0.12

Typical Mechanical UTS : 480 Mpa (N/mm²)

YS : 400 Mpa (N/mm²)

Properties of Weld Deposit Elongation % (I=5d) : 27

CVN Impact at -30° C : 60 Joules

Packing Specification: 500 and 1000mm cut length Packed in 5.0 kgs plastic corrugated tube.

ANAND ARC LTD.
(AN ISO 9001:2008 COMPANY)
701, Trade Centre Bandra Kurla Complex (BKC),
Bandra (E), Mumbai – 400 051.
Tel: +91-22-42688484, Fax: +91-22-42688400
E-mail : sales@anandarc.com / anand@anandarc.com
Website : www.anandarc.com

ANAND ARC PRODUCTS
More than a Sources, a Solution.



ANAND TIG-3
Copper Coated Solid Wire
For TIG Welding

Technical Data

Description: ANAND TIG - 3 is Copper coated carbon steel that contains well Balanced levels of manganese and silicon and is designed for use with various gas mixtures such as 100% CO₂, 75/25 Ar/CO₂, or 98/2 Ar/O₂. Yielding a slag free quality weld deposit, a smooth stable arc with low spatter and smooth flow.

Typical Application: Extensive use in the automotive structure, frame fabrication, construction equipments, pressure vessels, pipe fabrication, railcar construction and repair and also used in high speed robotic, automatic and semi automatic welding application.

Classification: AWS: A5.18/ER70S3

Sizes 1.60mm 2.00mm 2.50mm 3.15mm 4.00mm

Chemical Analysis (%)

C	Mn	Si	S	P	Cr	Ni	Mo	V	Cu
0.06-0.15	0.90-1.40	0.45-0.75	0.035 Max	0.025 Max	0.15 Max	0.15 Max	0.15 Max	0.03 Max	0.50 Max

Mechanical Properties Of All Weld Metal

UTS	Y.S	% Elongation	CVN
N/mm ²	N/mm ²	I=5d	at -20°C
480MPa (min)	400MPamin	22 min	27J min

Packing 500 and 1000mm cut length Packed in 5.0 kgs plastic corrugated tube.

ANAND ARC LTD.
(AN ISO 9001:2008 COMPANY)
701, Trade Centre Bandra Kurla Complex (BKC),
Bandra (E), Mumbai - 400 051.
Tel: +91-22-42688484, Fax: +91-22-42688400
E-mail : sales@anandarc.com / anand@anandarc.com
Website : www.anandarc.com

ANAND ARC PRODUCTS
More than a Sources, a Solution.